



HAL
open science

Comparison of Homogenization Schemes to Periodic and Random Simulations

Laurent Charpin, Florian Thomines, Alain Ehlacher

► **To cite this version:**

Laurent Charpin, Florian Thomines, Alain Ehlacher. Comparison of Homogenization Schemes to Periodic and Random Simulations. Netherlands. 2012. hal-00843902

HAL Id: hal-00843902

<https://enpc.hal.science/hal-00843902v1>

Submitted on 12 Jul 2013

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

COMPARISON OF HOMOGENIZATION SCHEMES TO PERIODIC AND RANDOM SIMULATIONS

Laurent Charpin¹ - laurent.charpin@enpc.fr, Florian Thomines², and Alain Ehlacher¹

1-Université Paris-Est, Laboratoire Navier (ENPC/IFSTTAR/CNRS), École des Ponts ParisTech, 6-8 avenue Blaise Pascal, 77455 Marne-la-Vallée, France

2-Ecole des Ponts, 77455 Marne-La-Valle Cedex 2 and INRIA, MICMAC project, 78153 Le Chesnay Cedex, France.

ASSESSMENT OF THE EFFICIENCY OF THE INTERACTION DIRECT DERIVATIVE HOMOGENIZATION SCHEME BY COMPARISON TO FINITE ELEMENT SIMULATIONS.

Average properties

At a macroscopic scale, for a porous medium with one pore family loaded with pressures p , the constitutive law writes [1]:

$$\begin{cases} \underline{\underline{\Sigma}} = \underline{\underline{C}}^{hom} : \underline{\underline{E}} - p\underline{\underline{B}} \\ \phi - f = \underline{\underline{B}} : \underline{\underline{E}} + pM \end{cases}$$

Where we call $\underline{\underline{C}}^{hom}$ the homogenized stiffness tensor, $\underline{\underline{B}}$ the Biot coefficient, and M the Biot modulus (inverse of the usual Biot modulus N).

Simulations using FreeFem++

We create a volume with pores in a 2d plane strain model, and apply:

- external loadings
- pressure in the pores

using periodic B.C., to determine the poroelastic constants by measurement of strain and stress averages.




Fig. 1: Elliptical inclusions on an elliptical grid, periodic simulation





Fig. 2: Circular inclusions in a random simulation


Estimates

- Mori-Tanaka: **MT** (Inclusion embedded in the matrix, averages computed on a domain of the same shape as the inclusion, respecting volume fractions)
- Interaction-Direct-Derivative: **IDD** (Convenient simplification of the generalized self-consistent scheme, in which the inclusion is embedded in the matrix atmosphere, which is embedded in the average medium [2])



Aligned elliptical pores, aspect ratio 0.1

We compare random simulations **simu**, periodic simulation with isotropic cell **perEC** and elliptic cell **perEE**, to the **IDD** scheme with circular atmosphere and the **MT** scheme. The **IDD** is failing because some coefficient reach their bound (0 or 1) far too early. **MT** does not show this problem. **IDD** needs to be used more carefully. **perEC** is accurate but cannot reach high volume fractions, **perEE** gives unsatisfactory results at intermediate volume fractions.



We modify the IDD scheme to improve the results according to a simple geometrical rule and an optimization procedure. The aspect ratio of the atmosphere $\frac{b^d}{a^d}$ needs to change from 1 to that of the inclusion 0.1 when the volume fraction f increases.





Fig. 3: Two possibilities for the evolution of the aspect ratio of the atmosphere





Fig. 4: Efficiency of this modification. (×): simulations, (●): geometrical rule, (---): optimized shape

The geometrical rule is less satisfactory than the optimized shape, but is simpler. We call the **IDD** estimate built by this modification **IDD-A**. It is not new [3].

Isotropically oriented elliptical pores, aspect ratio 0.1

Finally we compare three estimates to simulations in the case of randomly oriented pores. The results obtained with **IDD-A** are very satisfactory.



Conclusion

The **IDD** scheme, when used with adapted shapes for the atmospheres, gives good results to predict the homogenized properties of crack-like pores, whether aligned or isotropically oriented.

Acknowledgements

This work was prepared thanks to a funding from the Chaire Durabilité des Matériaux et des Structures pour l'Énergie at École des Ponts ParisTech.

References

- [1] Luc Dormieux, Djimédo Kondo, and Franz-Josef Ulm. *Microporomechanics*. Wiley, 2006.
- [2] Q.-S. Zheng and D.-X. DU. An explicit and universally applicable estimate for the effective properties of multiphase composites which accounts for inclusion distribution. *Journal of Mechanics and Physics of Solids*, 49:2765 – 2788, 2001.
- [3] P. Ponte Castaneda and J.R. Willis. The effect of spatial distribution on the effective behavior of composite materials and cracked media. *J. Mech. Phys. Solids*, 43 - 12:1919–1951, 1995.