



On stress-gradient materials: formulation and homogenization

Sébastien Brisard, Vinh Phuc Tran, Karam Sab, Johann Guilleminot

► To cite this version:

Sébastien Brisard, Vinh Phuc Tran, Karam Sab, Johann Guilleminot. On stress-gradient materials: formulation and homogenization. Encounter of the third kind on generalized continua and microstructures, Apr 2018, Arpino, Italy. hal-01758985

HAL Id: hal-01758985

<https://enpc.hal.science/hal-01758985>

Submitted on 5 Apr 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

On stress-gradient materials: formulation and homogenization

S. Brisard¹, V.P. Tran^{1,2}, K. Sab¹, J. Guilleminot³



¹Université Paris-Est, Laboratoire Navier, UMR 8205,
CNRS, ENPC, IFSTTAR, F-77455 Marne-la-Vallée, France

²Université Paris-Est, Laboratoire Modélisation et Simulation Multi Échelle
(MSME), UMR 8208, CNRS, F-77454 Marne-la-Vallée, France

³Department of Civil and Environmental Engineering, Duke University,
Durham, NC 27708, USA

4 April 2018



Stress-gradient elasticity in a nutshell

The Stress Principle of Cauchy

$$\boldsymbol{\sigma} \cdot \nabla + \mathbf{b} = \mathbf{0} \quad \text{and} \quad [\![\boldsymbol{\sigma}]\!] \cdot \mathbf{n} = \mathbf{0} \quad (\text{SA})$$

Cauchy elasticity

$$W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}) dV$$

Stress-gradient elasticity

$$W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}, \boldsymbol{\sigma} \otimes \nabla) dV$$

A mature model

[Forest and Sab \(2012\)](#), Mechanics Research Communications 40

(first derivation)

[Sab, Legoll and Forest \(2016\)](#), Journal of Elasticity 123(2)

(mathematical justification)

[Forest and Sab \(2017\)](#), Mathematics and Mechanics of Solids

(extension to finite strain)

Alternative model (not discussed here)

[Polizzotto \(2014, 2016\)](#), International Journal of Solids and Structures

In the present talk

A brief overview of the stress-gradient model

- ▶ Decomposition of the stress-gradient
- ▶ Stress boundary conditions

Homogenization of stress-gradient materials

- ▶ Hill–Mandel lemma, boundary conditions
- ▶ Softening size effect

Application to composites with spherical inclusions

- ▶ Eshelby’s inhomogeneity problem
- ▶ Mori–Tanaka estimates of effective compliance

[Tran, Brisard, Guilleminot and Sab \(2018\)](#), International Journal of Solids and Structures

Some open questions

Derivation of the stress-gradient model for elasticity

Roadmap

Minimize complementary stress energy under SA constraint

- ▶ Cauchy elasticity: elastic equilibrium of fixed solid is retrieved
- ▶ Stress-gradient elasticity: elastic equilibrium of fixed solid is **defined**
- ▶ At this point, “fixed” not really meaningful, since dofs not (yet) defined
- ▶ “Trace” of the stress-gradient is prescribed

Decomposition of stress-gradient (1/2)

Complementary stress energy of stress-gradient materials

$$W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}, \boldsymbol{\sigma} \otimes \nabla) dV$$

Classical equilibrium equation

$$(\boldsymbol{\sigma} \otimes \nabla) : \mathbf{I}_2 = \boldsymbol{\sigma} \cdot \nabla = -\mathbf{b}$$

Orthogonal decomposition of stress gradient

$$\boldsymbol{\sigma} \otimes \nabla = \mathbf{Q} + \mathbf{R} \quad \text{with} \quad \mathbf{R} : \mathbf{I}_2 = 0 \quad \text{and} \quad \mathbf{Q} : \mathbf{R} = 0$$

$$\mathbf{R} = \mathbf{I}'_6 \therefore (\boldsymbol{\sigma} \otimes \nabla) \quad \text{(projection onto space of trace-free, third-rank tensors)}$$

Equivalent expression of complementary stress energy

$$W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}, \mathbf{Q}, \mathbf{R}) dV$$

Decomposition of stress-gradient (2/2)

Orthogonal decomposition of stress gradient

$$\boldsymbol{\sigma} \otimes \nabla = \mathbf{Q} + \mathbf{R} \quad \text{with} \quad \mathbf{R} : \mathbf{I}_2 = 0 \quad \text{and} \quad \mathbf{Q} : \mathbf{R} = 0$$

\mathbf{Q} is in fact fully prescribed

$$\mathbf{Q} = -\frac{1}{2} \mathbf{I}_4 \cdot \mathbf{b} \quad (\text{straightforward linear algebra})$$

No strain measure attached to \mathbf{Q} (generalized prestress)

Modeling assumption

$$W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}, \mathbf{Q}, \mathbf{R}) dV = \int w^c(\boldsymbol{\sigma}, \mathbf{R}) dV$$

$$\text{with } \mathbf{R} = \mathbf{I}'_6 \therefore (\boldsymbol{\sigma} \otimes \nabla)$$

Constrained minimization of energy

Initial problem

$$\text{Minimize: } W^c[\boldsymbol{\sigma}] = \int w^c(\boldsymbol{\sigma}, \mathbf{I}'_6 : (\boldsymbol{\sigma} \otimes \nabla)) dV$$

$$\text{subject to: } \boldsymbol{\sigma} \cdot \nabla + \mathbf{b} = \mathbf{0}$$

Stress-gradient as independent variable

$$\text{Minimize: } W^c[\boldsymbol{\sigma}, \mathbf{R}] = \int w^c(\boldsymbol{\sigma}, \mathbf{R}) dV$$

$$\text{subject to: } \begin{cases} \boldsymbol{\sigma} \cdot \nabla + \mathbf{b} = \mathbf{0} \\ \mathbf{R} = \mathbf{I}'_6 : (\boldsymbol{\sigma} \otimes \nabla) \end{cases} \quad \cdot \mathbf{u} \quad \therefore \Phi$$

Lagrange
multipliers

Elastic equilibrium of fixed, SG bodies

Field equations

$$\boldsymbol{\sigma} \cdot \nabla + \mathbf{b} = 0$$

$$\mathbf{R} = \mathbf{I}'_6 \therefore (\boldsymbol{\sigma} \otimes \nabla)$$

Generalized equilibrium equations

$$\mathbf{e} = \partial_{\boldsymbol{\sigma}} w^c$$

$$\boldsymbol{\Phi} = \partial_{\mathbf{R}} w^c$$

Generalized stress-strain relations

$$\mathbf{e} = \boldsymbol{\Phi} \cdot \nabla + \boldsymbol{\varepsilon}[u]$$

Generalized strain-displacement relations

Boundary conditions

$$\boldsymbol{\Phi} \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n}) = 0$$

6 scalar boundary conditions

Continuity conditions

$$[\![\boldsymbol{\Phi} \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n})]\!] = 0$$

Weaker continuity of “displacements”

$$[\![\boldsymbol{\sigma}]\!] = 0$$

Stronger continuity of “stresses”

Linear elasticity

Complementary stress energy density

$$w^c(\boldsymbol{\sigma}, \mathbf{R}) = \frac{1}{2} \boldsymbol{\sigma} : \mathbf{S} : \boldsymbol{\sigma} + \frac{1}{2} \mathbf{R} : \mathbf{M} : \mathbf{R}$$

No $\boldsymbol{\sigma}$ - \mathbf{R} coupling for centrosymmetric materials!

\mathbf{S} and \mathbf{M} have major and minor symmetries

Generalized compliance \mathbf{M} operates on trace-free tensors

$$\mathbf{M} = \mathbf{I}'_6 : \mathbf{M} : \mathbf{I}'_6$$

Stress-strain relationships

$$\mathbf{e} = \mathbf{S} : \boldsymbol{\sigma} \quad \text{and} \quad \Phi = \mathbf{M} : \mathbf{R}$$

or

$$\mathbf{C} = \mathbf{S}^{-1} \quad \text{and} \quad \mathbf{L} = \mathbf{M}^+$$

$$\boldsymbol{\sigma} = \mathbf{C} : \mathbf{e} \quad \text{and} \quad \mathbf{R} = \mathbf{L} : \Phi$$

Isotropic linear elasticity

General isotropic linear stress-gradient elasticity

$$\mathbf{M} = \mathbf{I}'_6 \therefore \mathbf{M} \therefore \mathbf{I}'_6$$

$$2\mu\mathbf{M} = \ell_J^2 \mathbf{J}_6 + \ell_K^2 \mathbf{K}_6 + \ell_H^2 \mathbf{H}_6$$

$$\mathbf{I}'_6 = \mathbf{J}_6 + \mathbf{K}_6$$

\ddots	\mathbf{J}_6	\mathbf{K}_6	\mathbf{H}_6
\mathbf{J}_6	\mathbf{J}_6	$\mathbf{0}$	$\mathbf{0}$
\mathbf{K}_6	$\mathbf{0}$	\mathbf{K}_6	\mathbf{H}_6
\mathbf{H}_6	$\mathbf{0}$	\mathbf{H}_6	\mathbf{H}_6

Simplified model for isotropic linear stress-gradient elasticity

$$2\mu\mathbf{S} = \frac{1-2\nu}{1+\nu} \mathbf{J}_4 + \mathbf{K}_4$$

$$\frac{2\mu}{\ell^2} \mathbf{M} = \frac{1-2\nu}{1+\nu} \mathbf{J}_6 + \mathbf{K}_6$$

Altan and Aifantis (1992), Scripta Metallurgica et Materialia 26(2)

Altan and Aifantis (1997), Journal of the Mechanical behavior of Materials 8(3)

Gao and Park (2007), International Journal of Solids and Structures 44

Homogenization


Setting the stage for homogenization

The 3 cases

- ▶ Stress-gradient (micro) → stress-gradient (macro)
- ▶ Cauchy (micro) → stress-gradient (macro)
- ▶ **Stress-gradient (micro) → Cauchy (macro)**

Separation of scales

- ▶ Classical condition



- ▶ Additional condition for stress-/strain- gradient materials

$$\ell \sim d \quad \text{or} \quad \ell \ll d$$

Material internal length

Effective and apparent properties

Effective behaviour: stress-gradient \rightarrow Cauchy $(\ell \sim d)$

$$\langle \mathbf{e} \rangle = \mathbf{S}^{\text{eff}} : \langle \boldsymbol{\sigma} \rangle$$

Apparent elastic properties of (large) SVE Ω

$$\langle \boldsymbol{\sigma} \rangle = \frac{1}{V} \int_{\Omega} \boldsymbol{\sigma} dV$$

$$\langle \mathbf{e} \rangle = \mathbf{S}^{\text{app}}(\Omega) : \langle \boldsymbol{\sigma} \rangle$$

$$\langle \mathbf{e} \rangle = \frac{1}{V} \int_{\Omega} \mathbf{e} dV = \frac{1}{V} \int_{\Omega} \boldsymbol{\varepsilon}[u] dV + \frac{1}{V} \int_{\partial\Omega} \boldsymbol{\Phi} \cdot \mathbf{n} dS$$

Local problem on SVE Ω

$$\boldsymbol{\sigma} \cdot \nabla = 0$$

No body forces!

$$\mathbf{e} = \mathbf{S} : : \boldsymbol{\sigma}$$

$$\boldsymbol{\Phi} = \mathbf{M} : : (\boldsymbol{\sigma} \otimes \nabla)$$

+ boundary conditions!

$$\mathbf{e} = \boldsymbol{\Phi} \cdot \nabla + \boldsymbol{\varepsilon}[u]$$

Boundary conditions

Generalized Hill–Mandel lemma

$$\langle \boldsymbol{\sigma}^* : \mathbf{e} + (\boldsymbol{\sigma}^* \otimes \nabla) : : \boldsymbol{\Phi} \rangle = \langle \boldsymbol{\sigma}^* \rangle : \langle \mathbf{e} \rangle$$

Uniform stress boundary conditions

$$\boldsymbol{\sigma}|_{\partial\Omega} = \bar{\boldsymbol{\sigma}}$$

$$\langle \mathbf{e} \rangle = \mathbf{S}^\sigma(\Omega) : \langle \boldsymbol{\sigma} \rangle = \mathbf{S}^\sigma(\Omega) : \bar{\boldsymbol{\sigma}}$$

Uniform strain boundary conditions

$$\boldsymbol{\Phi} \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n}) = \text{sym}[(\bar{\mathbf{e}} \cdot \mathbf{x}) \otimes \mathbf{n}]$$

$$\langle \boldsymbol{\sigma} \rangle = \mathbf{C}^\varepsilon(\Omega) : \langle \mathbf{e} \rangle = \mathbf{C}^\varepsilon(\Omega) : \bar{\mathbf{e}}$$

Uniform traction boundary conditions

$$\boldsymbol{\sigma}|_{\partial\Omega} \cdot \mathbf{n} = \bar{\boldsymbol{\sigma}} \cdot \mathbf{n}$$

$$\langle \mathbf{e} \rangle = \mathbf{S}^T(\Omega) : \langle \boldsymbol{\sigma} \rangle = \mathbf{S}^T(\Omega) : \bar{\boldsymbol{\sigma}}$$

$$\mathbf{a} \cdot [\boldsymbol{\Phi} \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n})] \cdot \mathbf{a} = 0$$

$$\mathbf{a} = \mathbf{I}_2 - \mathbf{n} \otimes \mathbf{n}$$

Variational formulation

Minimum of complementary stress energy

$$\bar{\boldsymbol{\sigma}} : \mathbf{S}^\sigma(\Omega) : \bar{\boldsymbol{\sigma}} = \inf \{ \langle \boldsymbol{\sigma} : \mathbf{S} : \boldsymbol{\sigma} + (\boldsymbol{\sigma} \otimes \nabla) : : \mathbf{M} : : (\boldsymbol{\sigma} \otimes \nabla) \rangle \}$$

subject to: $\boldsymbol{\sigma} \cdot \nabla = \mathbf{0}$ and $\boldsymbol{\sigma}|_{\partial\Omega} = \bar{\boldsymbol{\sigma}}$

Minimum of strain energy

$$\bar{\mathbf{e}} : \mathbf{C}^\varepsilon(\Omega) : \bar{\mathbf{e}} = \inf \{ \langle \boldsymbol{\varepsilon}[\mathbf{u}] : \mathbf{C} : \boldsymbol{\varepsilon}[\mathbf{u}] + \boldsymbol{\Phi} : : \mathbf{L} : : \boldsymbol{\Phi} \rangle \}$$

subject to: $\boldsymbol{\Phi} \cdot \mathbf{n} + \mathbf{sym}(\mathbf{u} \otimes \mathbf{n}) = \mathbf{sym}[(\bar{\mathbf{e}} \cdot \mathbf{x}) \otimes \mathbf{n}]$

Bounds for finite-size SVEs

$$\mathbf{C}^\sigma(\Omega_I) \leq \mathbf{C}^\sigma(\Omega_{II}) \leq \mathbf{C}^{\text{eff}} \leq \mathbf{C}^\varepsilon(\Omega_{II}) \leq \mathbf{C}^\varepsilon(\Omega_I) \quad \text{for } \Omega_I \subset \Omega_{II}$$

Softening size-effect

Variational definition of apparent compliance (uniform σ BC)

If $\mathbf{S}_I \leq \mathbf{S}_{II}$ and $\mathbf{M}_I \leq \mathbf{M}_{II}$ everywhere in Ω , then $\mathbf{S}_I^{\text{eff}} \leq \mathbf{S}_{II}^{\text{eff}}$

Fixed microstructure, variable material internal length

For $\mathbf{S}_I = \mathbf{S}_{II}$ and $\mathbf{M}_I = \frac{\ell_I^2}{\ell_{II}^2} \mathbf{M}_{II}$: if $\ell_I \leq \ell_{II}$ then $\mathbf{S}_I^{\text{eff}} \leq \mathbf{S}_{II}^{\text{eff}}$

More generally: if $\left(\frac{\ell}{d}\right)_I \leq \left(\frac{\ell}{d}\right)_{II}$ then $\mathbf{S}_I^{\text{eff}} \leq \mathbf{S}_{II}^{\text{eff}}$

Scaled microstructure, constant material internal length

If $d_I \leq d_{II}$ then $\mathbf{C}_I^{\text{eff}} \leq \mathbf{C}_{II}^{\text{eff}}$


Softening size-effect!

Eshelby's inhomogeneity problem for stress-gradient elasticity

Problem setting

Matrix: μ_m, v_m, ℓ_m


$$\sigma^\infty e_z$$



$$v_i = v_m = 0.25$$

$$\mu_i = 10 \mu_m$$

$$-\sigma^\infty e_z$$







Some tedious calcs later...



<http://www.sympy.org>




Axial stress along vertical axis




Axial stress at origin

Theorem of Eshelby (1957) does not hold!

Dilute stress concentration tensor



Axial stress along vertical axis




Axial stress at origin

$$\langle \boldsymbol{\sigma} \rangle_i = \frac{1}{V_i} \int_{\Omega_i} \boldsymbol{\sigma} dV = \mathbf{B}^\infty : \boldsymbol{\sigma}^\infty$$


Mori–Tanaka estimates for composites with spherical inclusions

Problem setting




Volume fraction of inclusions: f

Estimates of bulk and shear moduli



Effective bulk modulus



Effective shear modulus

$$\mathbf{S}_{\text{eff}} = \mathbf{S}_m + f (\mathbf{S}_i - \mathbf{S}_m) : \mathbf{B}^\infty : [(1-f) \mathbf{I}_4 + f \mathbf{B}^\infty]^{-1}$$

Strain- and stress- gradient models are not equivalent!

Benveniste (1987), Mechanics of Materials 6(2)

Ma and Gao (2014), Acta Mechanica 225(4-5)

Some questions

The total complementary energy

Assumption 1: Stress Principle of Cauchy

$$\boldsymbol{\sigma} \cdot \nabla = 0 \text{ and } \boldsymbol{\sigma} \cdot \mathbf{n}|_{\partial\Omega} = \bar{T}$$


Assumption 2: complementary work
of prescribed displacements

$$V^c = \int_{\partial\Omega_u} \bar{u} \cdot \boldsymbol{\sigma} \cdot \mathbf{n} dS$$

Minimization of complementary energy

$$\text{Minimize: } \Pi^c = W^c - V^c$$

$$\text{subject to: } \boldsymbol{\sigma} \cdot \nabla = 0 \text{ and } \boldsymbol{\sigma} \cdot \mathbf{n}|_{\partial\Omega} = \bar{T}$$



The general BVP

Field equations

$$\boldsymbol{\sigma} \cdot \nabla + \mathbf{b} = \mathbf{0}$$

$$\mathbf{R} = \mathbf{I}'_6 \because (\boldsymbol{\sigma} \otimes \nabla)$$

$$\mathbf{e} = \partial_{\boldsymbol{\sigma}} w^c$$

$$\Phi = \partial_{\mathbf{R}} w^c$$

$$\mathbf{e} = \Phi \cdot \nabla + \boldsymbol{\varepsilon}[u]$$

Boundary conditions

$$\partial \Omega_T: \begin{cases} \boldsymbol{\sigma} \cdot \mathbf{n} \Big|_{\partial \Omega} = \bar{T} \\ \mathbf{a} \cdot [\Phi \cdot \mathbf{n} + \text{sym}(u \otimes \mathbf{n})] \cdot \mathbf{a} = 0 \end{cases}$$

$$\mathbf{a} = \mathbf{I}_2 - \mathbf{n} \otimes \mathbf{n}$$

$$\partial \Omega_u: \Phi \cdot \mathbf{n} + \text{sym}(u \otimes \mathbf{n}) = \text{sym}(\bar{u} \otimes \mathbf{n})$$

Continuity conditions

$$[\![\boldsymbol{\sigma}]\!] = 0$$

$$[\![\Phi \cdot \mathbf{n} + \text{sym}(u \otimes \mathbf{n})]\!] = 0$$

The total potential energy

Potential strain energy

$$W = \int w(\mathbf{e}, \Phi) dV$$

Work of prescribed body forces and tractions

$$V = \int_{\Omega} \mathbf{b} \cdot \mathbf{u} dV + \int_{\partial\Omega_T} \bar{\mathbf{T}} \cdot [\mathbf{u} + 2\Phi : \mathbf{n} \otimes \mathbf{n} - (\Phi : \mathbf{n} \otimes \mathbf{n} \otimes \mathbf{n}) \mathbf{n}] dS$$

Minimization of total potential energy

$$\text{Minimize: } \Pi = W - V$$

$$\mathbf{u} + 2\Phi : \mathbf{n} \otimes \mathbf{n} - (\Phi : \mathbf{n} \otimes \mathbf{n} \otimes \mathbf{n}) \mathbf{n} = \bar{\mathbf{u}}$$

subject to:
$$\begin{cases} \partial\Omega_T: \mathbf{a} \cdot [\Phi \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n})] \cdot \mathbf{a} = 0 \\ \partial\Omega_u: \Phi \cdot \mathbf{n} + \text{sym}(\mathbf{u} \otimes \mathbf{n}) = \text{sym}(\bar{\mathbf{u}} \otimes \mathbf{n}) \end{cases}$$

Conclusion & perspectives

Summary

- ▶ Simplified model for isotropic linear elasticity
- ▶ General framework for stress-gradient → Cauchy homogenization
- ▶ Softening size-effect
- ▶ Mori–Tanaka estimates for spherical inclusions

Outlook

- ▶ Hashin–Shtrikman (size-dependent) bounds on effective properties
- ▶ Cauchy → stress-gradient homogenization
- ▶ Understand the meaning of \mathbf{u} (use above)

Thanks for your attention!

Sebastien.brisard@ifsttar.fr
<http://navier.enpc.fr/BRISARD-Sebastien>
<http://sbrisard.github.io>



This work has benefited from a French government grant managed by ANR within the frame of the national program Investments for the Future ANR-11-LABX-022-01.



This work is licensed under the Creative Commons Attribution 4.0 International License. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/> or send a letter to Creative Commons, PO Box 1866, Mountain View, CA 94042, USA.