



HAL
open science

A micromechanical model for polycrystalline shape memory alloy wires integrated into smart structures

Philippe Hannequart, Michaël Peigney, Jean-François Caron, Emmanuel Viglino, Olivier Baverel

► **To cite this version:**

Philippe Hannequart, Michaël Peigney, Jean-François Caron, Emmanuel Viglino, Olivier Baverel. A micromechanical model for polycrystalline shape memory alloy wires integrated into smart structures. 11th European Symposium on Martensitic Transformations (ESOMAT 2018), Aug 2018, Metz, France. hal-01943168

HAL Id: hal-01943168

<https://enpc.hal.science/hal-01943168>

Submitted on 3 Dec 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

A MICROMECHANICAL MODEL FOR POLYCRYSTALLINE SHAPE MEMORY ALLOY WIRES INTEGRATED INTO SMART STRUCTURES

PHILIPPE HANNEQUART^{1,2}, MICHAEL PEIGNEY², JEAN-FRANCOIS CARON²,
EMMANUEL VIGLINO¹, OLIVIER BAVEREL²

¹ Arcora, Groupe Ingérop, Rueil-Malmaison, France

² Université Paris-Est, Laboratoire Navier (UMR 8205), CNRS, Ecole des Ponts ParisTech, IFSTTAR, 77455
Marne la vallée, France

ABSTRACT

This research aims at providing a computationally efficient one-dimensional micromechanical model for polycrystalline shape memory alloy (SMA) wires. The texture is described by a set of crystalline orientations along with their volume fraction. In the present work, each orientation relates to the martensitic transformation strain of its most favorably oriented martensitic variant (with respect to the loading direction), projected onto the wire axis. Two internal state variables characterize each crystalline orientation: the volume fraction of self-accommodated martensite, and the volume fraction of the most favorably oriented martensitic variant. The one-dimensional mechanical model of the wire in traction thus considers the influence of the 3-dimensional texture. This model can describe superelasticity, self-accommodation and reorientation of martensite, as well as the one-way shape memory effect. It has been implemented numerically in a user-material subroutine (UMAT) for the finite element software ABAQUS, resorting to numerical constrained optimization tools. Several thermomechanical experiments on Nickel-Titanium wires have been carried out in order to identify the model parameters and the wire texture. The model can be used to simulate the response of morphing structures including SMA wires, actuated by shape memory effect.

KEYWORDS: SHAPE MEMORY ALLOY. POLYCRYSTALL. WIRE.

INTRODUCTION

Thermomechanical models for shape memory alloys (SMA) can be categorized into phenomenological models and micromechanical models. Most micromechanical SMA models are 3-dimensional, computationally intensive and can only hardly be implemented in engineering codes to model smart structures. Some attempts at developing a simplified one-dimensional model have been made but often lack robustness [Nae, 2003]. The SMA behavior is usually modelled by using a free energy with constrained state variables, which makes the numerical implementation delicate. This research aims at providing a computationally efficient one-dimensional micromechanical model for polycrystalline SMA wires. The texture of Nickel-Titanium wires has been chosen in this study.

FORMULATION OF THE MODEL

The material is studied in form of a one-dimensional wire with n different possible grain orientations, the martensite phase being under the form of lattice correspondent variants. We thus have the 12 different martensitic variants of the Nickel-Titanium alloy. Secondly, we make the assumption that each grain, when submitted to a load increment (mechanical or thermal) which is sufficient to trigger the phase change, deforms in the direction of its most favorably oriented martensitic variant [Shu, 1998]. This deformation will then be projected on the wire axis and represent the transformation strain. Each grain orientation i is characterized by its maximal phase transformation strain ε_{tr}^i , its self-accommodated martensite volume fraction θ_{0i} , and its oriented martensite volume fraction θ_{1i} (the volume fraction of austenite in grain i is thus given by $1 - \theta_{0i} - \theta_{1i}$). The following material parameters were adopted for the Nickel-Titanium wire :

- E the Young's modulus (considered equal in all grains, in austenite as well as martensite variants)
- λ the latent heat term
- T_0 a reference temperature
- G_0 a dissipation parameter, corresponding to the self-accommodated martensite phase
- G_1 a dissipation parameter, corresponding to the oriented martensite phase (with $G_0 < G_1$)

We model the thermomechanical behavior of the shape memory alloy by the following free energy :

$$w(\varepsilon, \Theta, T) = \frac{1}{2} \cdot E \left(\varepsilon - \sum_1^n \theta_{1i} \cdot \varepsilon_{tr}^i \right)^2 + \lambda \frac{T - T_0}{T_0} \sum_{i=1}^n (\theta_{0i} + \theta_{1i}) \quad (1)$$

Where ε is the wire strain in the direction of traction and T is the wire temperature. The first term in (1) is the strain energy contribution, and the second term is the latent heat contribution. We adopt the framework of non-smooth thermodynamics [Fremond, 2001] and postulate the following dissipation potential which is convex and positive :

$$\Phi(\dot{\Theta}) = \sum_{i=1}^n G_0 |\dot{\theta}_{0i}| + G_1 |\dot{\theta}_{1i}| \quad (2)$$

This model requires the determination of the parameters ε_{tr}^i which we call texture parameters. They enable the model

to capture the non-linear hardening effect at the end of the phase change on stress-strain curves (Figure 1).

NUMERICAL IMPLEMENTATION

For monotonic loading cases, it is possible to obtain analytical solutions, but complex loading paths require a numerical implementation of the problem. Writing down the time discretization of the equations leads to a nonlinear incremental problem. By means of a change of variables, it can be rewritten as a Linear Complementarity Problem (LCP) as it has been made in [Peigney, 2011] for a 3-dimensional monocrystal. In this case, we can take advantage of the sparsity of the resulting matrix and use interior-point algorithms to solve the LCP. We can thus obtain the updated internal variables θ_{0i} and θ_{1i} for a given load or temperature increment. The algorithm has been implemented on MATLAB, and a user-material subroutine based on this algorithm has been developed for the finite-element software ABAQUS, enabling to study structures containing SMA wires.

EXPERIMENTAL VALIDATION

The model has been compared to traction tests which have been carried out on SMA wires in a controlled temperature environment (a water bath). Before testing, the wire underwent thermomechanical cycling in order to test the stabilized behavior. More specifically, the non-linear hardening during the phase change (Figure 1) has been observed and exploited to obtain the texture parameters of the SMA. Constant stress experiments with thermal loading have also been realized, highlighting the shape memory effect.




Figure 1: Traction test on a SMA wire at 45°C and polycrystalline simulation with 50 grain orientations (MATLAB)

CONCLUSION

A robust numerical SMA model has been formulated, numerically implemented and confronted to experimental data. It describes the main thermomechanical phenomena involved in shape memory alloys when used as actuators, but the model could be enhanced by developing a three dimensional version or by taking into account thermal expansion, the different elastic moduli of austenite and martensite, creep and stress relaxation, loading rate dependency, etc...

Acknowledgment

This work has been partially funded by Arcora & Ingérop Group and by ANRT under CIFRE grant No 2015/0495.

REFERENCES

- [Fremont, 2001] M. Fremont, Non-Smooth Thermomechanics, Berlin, Heidelberg: Springer, 2001.
- [Nae, 2003] F. Nae, Y. Matsuzaki and T. Ikeda, "Micromechanical modeling of polycrystalline shape-memory alloys including thermo-mechanical coupling", Smart Materials and Structures, 12, 1, 2003.
- [Peigney, 2011] M. Peigney, J.P. Seguin and E. Hervé-Luanco, "Numerical simulation of shape memory alloys structures using interior-point methods", International Journal of Solids and Structures, 48, 20, 2011, 2791 - 2799.
- [Shu, 1998] Y.C. Shu and K. Bhattacharya, "The influence of texture on the shape-memory effect in polycrystals", Acta Materialia, 46, 15, 1998, 5457 - 5473.