

On the spatial discretization of the Lippmann–Schwinger equation

Sébastien Brisard

Laboratoire Navier (UMR 8205),
École des Ponts, Université Gustave Eiffel, IFSTTAR, CNRS, Marne-la-Vallée, France

26 January 2021



Motivation (1/2)

Outline of the Moulinec–Suquet method

- **Step 1** – Start from the corrector problem (system of PDEs)
- **Step 2** – Reformulate as an integral equation (Lippmann–Schwinger)
- **Step 3** – Replace Fourier series with discrete Fourier transforms
- **Step 4** – Introduce fixed-point iterations

We recognize a familiar pattern

- **Step 3** is the **discretization** step
- **Step 4** is the **solution** step (introduces an iterative linear solver)

Motivation (2/2)

Questions

- Convergence with respect to grid size? **(S. Brisard)**
 - Investigation of the **spatial discretization** (this talk)
 - Cast the method in a Galerkin setting
- Convergence of the **iterative solver**? **(M. Schneider)**
 - How to minimize number of iterations?
 - Can we do better than fixed-point iterations
- Strategies for complex material non-linearities? **(L. Gélébart)**
 - Use condensed potential (M. Schneider)
 - Alternative approach

Outline of this talk

This talk is devoted to the spatial discretization of the Lippmann–Schwinger equation

- Introducing the corrector problem
- Preliminaries
- The periodic, fourth-rank Green operator
- Strong and weak forms of the Lippmann–Schwinger (LS) equation
- Discretization of the LS equation
- Connexion with the discrete Fourier transform
- Consistent vs. asymptotically consistent discretizations

Introducing the corrector problem

- The corrector problem
- On periodic boundary conditions

The “corrector” problem

Field equations

$$\operatorname{div} \boldsymbol{\sigma} = \mathbf{0}$$

$$\boldsymbol{\sigma} = \mathbf{C} : \boldsymbol{\varepsilon}$$


$$\boldsymbol{\varepsilon} = \operatorname{sym} \operatorname{grad} \mathbf{u}$$

\mathbf{C} depends on observation point
(material is heterogeneous!)

Periodic boundary conditions


$$\Omega = (0, L_1) \times \cdots \times (0, L_d)$$

$$\text{PBC}\{\bar{\boldsymbol{\varepsilon}}\} \stackrel{\text{def}}{=} \begin{cases} \mathbf{u}(\mathbf{x}) - \bar{\boldsymbol{\varepsilon}} \cdot \mathbf{x} & \Omega\text{-periodic} \\ \boldsymbol{\sigma}(\mathbf{x}) \cdot \mathbf{n}(\mathbf{x}) & \Omega\text{-skew-periodic} \end{cases}$$



On periodic boundary conditions

$$\text{PBC}\{\bar{\boldsymbol{\varepsilon}}\} \stackrel{\text{def}}{=} \begin{cases} \mathbf{u}(\mathbf{x}) - \bar{\boldsymbol{\varepsilon}} \cdot \mathbf{x} & \Omega\text{-periodic} \\ \boldsymbol{\sigma}(\mathbf{x}) \cdot \mathbf{n}(\mathbf{x}) & \Omega\text{-skew-periodic} \end{cases}$$



- 2nd condition should be understood as

$$\boldsymbol{\sigma}(\mathbf{x} + L_i \mathbf{e}_i) \cdot \mathbf{e}_i = \boldsymbol{\sigma}(\mathbf{x}) \cdot \mathbf{e}_i \quad \text{for all } i = 1, \dots, d$$

(no summation)

- $\bar{\boldsymbol{\varepsilon}}$ (prescribed) is the macroscopic strain: $\langle \boldsymbol{\varepsilon} \rangle = \bar{\boldsymbol{\varepsilon}}$
- Hill–Mandel lemma holds!

Preliminaries

- On the Mandel–Voigt representation of tensors
- On Fourier series
- On the discrete Fourier transform
- Fourier series vs. discrete Fourier transforms

Mandel–Voigt representation of tensors

2nd order, symmetric, tensors

$$[\mathbf{s}] = [s_{11}, s_{22}, s_{33}, \Xi s_{23}, \Xi s_{31}, \Xi s_{12}]^T \quad \text{with} \quad \Xi = \sqrt{2}$$

4th order tensors with minor symmetries

$$[\mathbf{T}] = \begin{bmatrix} T_{1111} & T_{1122} & T_{1133} & \Xi T_{1123} & \Xi T_{1131} & \Xi T_{1112} \\ T_{2211} & T_{2222} & T_{2233} & \Xi T_{2223} & \Xi T_{2231} & \Xi T_{2212} \\ T_{3311} & T_{3322} & T_{3333} & \Xi T_{3323} & \Xi T_{3331} & \Xi T_{3312} \\ \Xi T_{2311} & \Xi T_{2322} & \Xi T_{2333} & 2T_{2323} & 2T_{2331} & 2T_{2312} \\ \Xi T_{3111} & \Xi T_{3122} & \Xi T_{3133} & 2T_{3123} & 2T_{3131} & 2T_{3112} \\ \Xi T_{1211} & \Xi T_{1222} & \Xi T_{1233} & 2T_{1223} & 2T_{1231} & 2T_{1212} \end{bmatrix}$$

Some properties

$$\mathbf{s}_1 : \mathbf{s}_2 = [\mathbf{s}_1]^T \cdot [\mathbf{s}_2]$$

$$[\mathbf{T} : \mathbf{s}] = [\mathbf{T}] \cdot [\mathbf{s}]$$

$$[\mathbf{T}^{-1}] = [\mathbf{T}]^{-1}$$

On Fourier series

**Input data is a periodic function;
output data is an infinite, discrete set of numbers**

Discrete wave vectors over unit-cell $\Omega = (0, L_1) \times \dots \times (0, L_d)$

$$\mathbf{k}_n = \frac{2\pi n_1}{L_1} \mathbf{e}_1 + \dots + \frac{2\pi n_d}{L_d} \mathbf{e}_d$$

Fourier coefficients of a periodic function

$$\tilde{f}_n \stackrel{\text{def}}{=} \frac{1}{|\Omega|} \int_{\mathbf{x} \in \Omega} f(\mathbf{x}) e^{-i\mathbf{k}_n \cdot \mathbf{x}} dV_{\mathbf{x}}$$

Inversion (under mild regularity conditions)

$$f(\mathbf{x}) = \sum_{n \in \mathbb{Z}^d} \tilde{f}_n e^{i\mathbf{k}_n \cdot \mathbf{x}}$$

On the discrete Fourier transform (1/2)

Input and output data are finite sets of numbers

$(x_p)_p$ and $(\hat{x}_n)_n$ with $0 \leq p_i, n_i < N_i$ and $i = 1, \dots, d$

Definition

$$\hat{x}_n \stackrel{\text{def}}{=} \sum_{p_1=0}^{N_1-1} \cdots \sum_{p_d=0}^{N_d-1} x_p \exp\left[-2i\pi\left(\frac{p_1 n_1}{N_1} + \cdots + \frac{p_d n_d}{N_d}\right)\right]$$

Output can be seen as a discrete, periodic series

$$\hat{x}_{n+mN} = \hat{x}_n \quad \text{with} \quad n + mN \stackrel{\text{def}}{=} (n_1 + m_1 N_1, \dots, n_d + m_d N_d)$$

Implementation: fast Fourier transform (FFT)

$\mathcal{O}(N \log N)$ rather than $\mathcal{O}(N^2)$

On the discrete Fourier transform (2/2)

Inversion

$$x_p = \frac{1}{N_1 \cdots N_d} \sum_{n_1=0}^{N_1-1} \cdots \sum_{n_d=0}^{N_d-1} \hat{x}_n \exp \left[2i\pi \left(\frac{p_1 n_1}{N_1} + \cdots + \frac{p_d n_d}{N_d} \right) \right]$$

⇒ input can **also** be seen as a discrete, **periodic** series ($x_{p+qN} \stackrel{\text{def}}{=} x_p$).

Circular convolution theorem

$$\widehat{x \star y}_n = \hat{x}_n \hat{y}_n \quad \text{with} \quad (x \star y)_p \stackrel{\text{def}}{=} \sum_{q_1=0}^{N_1-1} \cdots \sum_{q_d=0}^{N_d-1} x_{p-q} y_q$$

Fourier series vs. DFT

Cell-wise constant functions (over a grid)

$$f|_{\Omega_p} = f_p \quad \text{and} \quad \langle f \rangle_p = f_p$$

Fourier coefficients of cell-wise constant functions

$$\tilde{f}_n = \frac{1}{N} F(h\mathbf{k}_n) \hat{f}_n \quad \text{with} \quad F(\mathbf{K}) = \text{sinc} \frac{K_1}{2} \dots \text{sinc} \frac{K_d}{2}$$

- \tilde{f}_n : Fourier coefficients of the **periodic function** f
- \hat{f}_n : discrete Fourier transform of the **cell values** f_p

Note: how to sum over \mathbb{Z}^d ?

$$\sum_{n \in \mathbb{Z}^d} \tilde{f}_n g_n = \sum_{0 \leq n_i < N_i} \hat{f}_n \left[\frac{1}{N} \sum_{m \in \mathbb{Z}^d} F(h\mathbf{k}_{n+mN}) g_{n+mN} \right]$$

The periodic, fourth-order Green operator

- Definition
- Elementary properties
- Expression in Fourier space

Definition

We consider here a homogeneous material!

The elementary problem

$$\left\{ \begin{array}{l} \operatorname{div} \boldsymbol{\sigma} = \mathbf{0} \\ \boldsymbol{\sigma} = \mathbf{C}_0 : \boldsymbol{\varepsilon} + \boldsymbol{\tau} \\ \boldsymbol{\varepsilon} = \operatorname{sym} \operatorname{grad} \mathbf{u} \\ \text{PBC}\{\bar{\boldsymbol{\varepsilon}}\} \end{array} \right. \quad \begin{array}{l} \text{Prescribed average strain is null!} \\ \mathbf{C}_0 = \text{const.} \\ \boldsymbol{\tau}(\mathbf{x}) \neq \text{const.} \end{array}$$

This is a linear problem

- Output depends **linearly** on input
- Loading parameters are $\bar{\boldsymbol{\varepsilon}}$ (const. tensor) and $\boldsymbol{\tau}$ (tensor field)

$$\boldsymbol{\varepsilon} = \mathbf{A} : \bar{\boldsymbol{\varepsilon}} - \boldsymbol{\Gamma}_0(\boldsymbol{\tau}) = \bar{\boldsymbol{\varepsilon}} - \boldsymbol{\Gamma}_0(\boldsymbol{\tau})$$

See Korringa [Kor73], Zeller and Dederichs [ZD73], and Kröner [Krö74]

Elementary properties

- Constant eigenstress: $\Gamma_0(\langle \boldsymbol{\tau} \rangle) = \mathbf{0}$
- Volume average: $\langle \Gamma_0(\boldsymbol{\tau}) \rangle = \mathbf{0}$
- Symmetry: $\langle \boldsymbol{\tau}_1 : \Gamma_0(\boldsymbol{\tau}_2) \rangle = \langle \Gamma_0(\boldsymbol{\tau}_1) : \boldsymbol{\tau}_2 \rangle$
- “Idempotence”: $\Gamma_0[\mathbf{C}_0 : \Gamma_0(\boldsymbol{\tau})] = \Gamma_0(\boldsymbol{\tau})$
- Positivity: $\langle \boldsymbol{\tau} : \Gamma_0(\boldsymbol{\tau}) \rangle \geq 0$

Γ_0 is a projector onto the space of
geometrically compatible strain fields

See Willis [[Wil77](#)] and Bellis and Suquet [[BS18](#)]

Expression in Fourier space

Use Fourier series expansions of all mechanical fields

$$\{\mathbf{u}(\mathbf{x}), \boldsymbol{\varepsilon}(\mathbf{x}), \boldsymbol{\sigma}(\mathbf{x}), \boldsymbol{\tau}(\mathbf{x})\} = \sum_{n \in \mathbb{Z}^d} \{\tilde{\mathbf{u}}_n, \tilde{\boldsymbol{\varepsilon}}_n, \tilde{\boldsymbol{\sigma}}_n, \tilde{\boldsymbol{\tau}}_n\} e^{i\mathbf{k}_n \cdot \mathbf{x}}$$

Expression of the Green operator in Fourier space

$$\tilde{\boldsymbol{\varepsilon}}_n = -\hat{\Gamma}_0(\mathbf{k}_n) : \tilde{\boldsymbol{\tau}}_n, \quad \text{with} \quad \hat{\Gamma}_0(\mathbf{k}) = \mathbf{I}_4 : [\mathbf{k} \otimes (\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k})^{-1} \otimes \mathbf{k}] : \mathbf{I}_4$$

In other words

$$\boldsymbol{\Gamma}_0(\boldsymbol{\tau})(\mathbf{x}) = \sum_{n \in \mathbb{Z}^d} \hat{\Gamma}_0(\mathbf{k}_n) : \tilde{\boldsymbol{\tau}}_n e^{i\mathbf{k}_n \cdot \mathbf{x}}$$

Note that $\hat{\Gamma}_0(\mathbf{k})$ does not depend on $\|\mathbf{k}\|$!

The dirty details (1/2)

- Rewrite BVP in Fourier space ($\mathbf{C}_0 = \text{const.}$ is **crucial!**)

$$\mathbf{div} \boldsymbol{\sigma} = \mathbf{0} \quad \longrightarrow \quad \tilde{\boldsymbol{\sigma}}_n \cdot i\mathbf{k}_n = \mathbf{0} \quad (1)$$

$$\boldsymbol{\sigma} = \mathbf{C}_0 : \boldsymbol{\varepsilon} + \boldsymbol{\tau} \quad \longrightarrow \quad \tilde{\boldsymbol{\sigma}}_n = \mathbf{C}_0 : \tilde{\boldsymbol{\varepsilon}}_n + \tilde{\boldsymbol{\tau}}_n \quad (2)$$

$$\boldsymbol{\varepsilon} = \mathbf{sym} \mathbf{grad} \mathbf{u} \quad \longrightarrow \quad \tilde{\boldsymbol{\varepsilon}}_n = \mathbf{sym}(\tilde{\mathbf{u}}_n \otimes i\mathbf{k}_n) \quad (3)$$

- Combine (2) and (3) (drop indices)

$$\left. \begin{array}{l} \tilde{\boldsymbol{\sigma}} = \mathbf{C}_0 : \tilde{\boldsymbol{\varepsilon}} + \tilde{\boldsymbol{\tau}} \\ \tilde{\boldsymbol{\varepsilon}} = \mathbf{sym}(\tilde{\mathbf{u}} \otimes i\mathbf{k}) \end{array} \right\} \Rightarrow \tilde{\boldsymbol{\sigma}} = (\mathbf{C}_0 \cdot i\mathbf{k}) \cdot \tilde{\mathbf{u}} + \tilde{\boldsymbol{\tau}}$$

- Plug into (1)

$$\tilde{\boldsymbol{\sigma}} \cdot i\mathbf{k} = \mathbf{0} \Rightarrow (\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k}) \cdot \tilde{\mathbf{u}} = i \tilde{\boldsymbol{\tau}} \cdot \mathbf{k}$$

The dirty details (2/2)

- General expression of displacement ($k = \|\mathbf{k}\|$ and $\mathbf{n} = \mathbf{k}/k$)

$$\begin{aligned}\tilde{\mathbf{u}} &= i(\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k})^{-1} \cdot \tilde{\boldsymbol{\tau}} \cdot \mathbf{k} \\ &= i[(\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k})^{-1} \otimes \mathbf{k}] : \tilde{\boldsymbol{\tau}} \\ &= i[(\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k})^{-1} \otimes \mathbf{k}] : (\mathbf{I}_4 : \tilde{\boldsymbol{\tau}}) \\ &= i\{[(\mathbf{k} \cdot \mathbf{C}_0 \cdot \mathbf{k})^{-1} \otimes \mathbf{k}] : \mathbf{I}_4\} : \tilde{\boldsymbol{\tau}} \\ &= ik^{-1}\{[(\mathbf{n} \cdot \mathbf{C}_0 \cdot \mathbf{n})^{-1} \otimes \mathbf{n}] : \mathbf{I}_4\} : \tilde{\boldsymbol{\tau}}\end{aligned}$$

- General expression of strain

$$\tilde{\boldsymbol{\varepsilon}} = \text{sym}(i\mathbf{k} \otimes \tilde{\mathbf{u}}) = \mathbf{I}_4 : (i\mathbf{k} \otimes \tilde{\mathbf{u}}) = -\hat{\boldsymbol{\Gamma}}_0 : \tilde{\boldsymbol{\tau}}$$

with

$$\hat{\boldsymbol{\Gamma}}_0 = \mathbf{I}_4 : [\mathbf{n} \otimes (\mathbf{n} \cdot \mathbf{C}_0 \cdot \mathbf{n})^{-1} \otimes \mathbf{n}] : \mathbf{I}_4 \quad (\text{QED})$$

Isotropic reference material

$$\mathbf{C}_0 = 2\mu_0 \left(\frac{1 + \nu_0}{1 - 2\nu_0} \mathbf{J}_4 + \mathbf{K}_4 \right) \quad \mathbf{J}_4 = \frac{1}{3} \mathbf{I}_2 \otimes \mathbf{I}_2 \quad \mathbf{K}_4 = \mathbf{I}_4 - \mathbf{J}_4$$

$$\mu_0^{-1} \mathbf{n} \cdot \mathbf{C}_0 \cdot \mathbf{n} = \mathbf{I}_2 + \frac{\mathbf{n} \otimes \mathbf{n}}{1 - 2\nu_0} = (\mathbf{I}_2 - \mathbf{n} \otimes \mathbf{n}) + \frac{2(1 - \nu_0)}{1 - 2\nu_0} \mathbf{n} \otimes \mathbf{n}$$

$$\mu_0 (\mathbf{n} \cdot \mathbf{C}_0 \cdot \mathbf{n})^{-1} = (\mathbf{I}_2 - \mathbf{n} \otimes \mathbf{n}) + \frac{1 - 2\nu_0}{2(1 - \nu_0)} \mathbf{n} \otimes \mathbf{n} = \mathbf{I}_2 - \frac{\mathbf{n} \otimes \mathbf{n}}{2(1 - \nu_0)}$$

$$\hat{\Gamma}_{0,ijkl}(\mathbf{k}) = \frac{\delta_{ik} n_j n_l + \delta_{il} n_j n_k + \delta_{jk} n_i n_l + \delta_{jl} n_i n_k}{4\mu_0} - \frac{n_i n_j n_k n_l}{2\mu_0 (1 - \nu_0)}$$

(applies also to plane strain elasticity)

The Lippmann–Schwinger equation

- Strong form of the LS equation
- Weak form of the LS equation
- The space of stress-polarizations

Derivation of the LS equation

Recall the corrector problem

$$\mathcal{P} \stackrel{\text{def}}{=} \begin{cases} \mathbf{div} \boldsymbol{\sigma} = \mathbf{0} \\ \boldsymbol{\sigma} = \mathbf{C} : \boldsymbol{\varepsilon} \\ \boldsymbol{\varepsilon} = \mathbf{sym} \mathbf{grad} \mathbf{u} \\ \text{PBC}\{\bar{\boldsymbol{\varepsilon}}\} \end{cases} \quad \begin{array}{l} \text{Heterogeneous material!} \\ \mathbf{C}(\mathbf{x}) \neq \text{const.} \end{array}$$

Introduce one new unknown... and one new equation

$$\mathcal{P} \iff \begin{cases} \mathbf{div} \boldsymbol{\sigma} = \mathbf{0} \\ \boldsymbol{\sigma} = \mathbf{C}_0 : \boldsymbol{\varepsilon} + \boldsymbol{\tau} \\ \boldsymbol{\varepsilon} = \mathbf{sym} \mathbf{grad} \mathbf{u} \\ \text{PBC}\{\bar{\boldsymbol{\varepsilon}}\} \\ \boldsymbol{\tau} = (\mathbf{C} - \mathbf{C}_0) : \boldsymbol{\varepsilon} \end{cases} \quad \begin{array}{l} \text{Arbitrary reference material} \\ \mathbf{C}_0 = \text{const.} \\ \boldsymbol{\tau}: \text{stress-polarization} \end{array}$$

Strong form of the LS equation

From Hervé's talk

$$\text{Corrector problem} \iff \begin{cases} \boldsymbol{\varepsilon} = \bar{\boldsymbol{\varepsilon}} - \Gamma_0(\boldsymbol{\tau}) \\ \boldsymbol{\tau} = (\mathbf{C} - \mathbf{C}_0) : \boldsymbol{\varepsilon} \end{cases}$$

LS equation: strong form #1

LS equation: strong form #2

$$\boldsymbol{\varepsilon} + \Gamma_0[(\mathbf{C} - \mathbf{C}_0) : \boldsymbol{\varepsilon}] = \bar{\boldsymbol{\varepsilon}}$$

$$(\mathbf{C} - \mathbf{C}_0)^{-1} : \boldsymbol{\tau} + \Gamma_0(\boldsymbol{\tau}) = \bar{\boldsymbol{\varepsilon}}$$

Simplify notation

$$\mathbf{L}(\mathbf{x}) \stackrel{\text{def}}{=} \mathbf{C}(\mathbf{x}) - \mathbf{C}_0 \quad \text{and} \quad \mathbf{M}(\mathbf{x}) = \mathbf{L}(\mathbf{x})^{-1}$$

See Korringa [Kor73], Zeller and Dederichs [ZD73], and Kröner [Krö74]

Weak form of the LS equation [Wil77]

Step 1 – Start from strong form of LS equation

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that, for all $\mathbf{x} \in \Omega$:

$$\mathbf{M}(\mathbf{x}) : \boldsymbol{\tau}(\mathbf{x}) + \Gamma_0(\boldsymbol{\tau})(\mathbf{x}) = \bar{\boldsymbol{\varepsilon}}$$

Step 2 – “Multiply” with arbitrary test stress-polarization

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that, for all $\mathbf{x} \in \Omega$ and $\boldsymbol{\varpi} \in \mathbb{V}$:

$$\boldsymbol{\varpi}(\mathbf{x}) : \mathbf{M}(\mathbf{x}) : \boldsymbol{\tau}(\mathbf{x}) + \boldsymbol{\varpi}(\mathbf{x}) : \Gamma_0(\boldsymbol{\tau})(\mathbf{x}) = \boldsymbol{\varpi}(\mathbf{x}) : \bar{\boldsymbol{\varepsilon}}$$

Step 3 – Integrate over unit-cell Ω (take volume average)

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that, for all $\boldsymbol{\varpi} \in \mathbb{V}$:

$$a(\boldsymbol{\tau}, \boldsymbol{\varpi}) \stackrel{\text{def}}{=} \langle \boldsymbol{\varpi} : \mathbf{M} : \boldsymbol{\tau} \rangle + \langle \boldsymbol{\varpi} : \Gamma_0(\boldsymbol{\tau}) \rangle = \langle \boldsymbol{\varpi} : \bar{\boldsymbol{\varepsilon}} \rangle \stackrel{\text{def}}{=} \ell(\boldsymbol{\varpi})$$

On the space of stress-polarizations

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that, for all $\boldsymbol{\varpi} \in \mathbb{V}$:

$$a(\boldsymbol{\tau}, \boldsymbol{\varpi}) \stackrel{\text{def}}{=} \langle \boldsymbol{\varpi} : \mathbf{M} : \boldsymbol{\tau} \rangle + \langle \boldsymbol{\varpi} : \boldsymbol{\Gamma}_0(\boldsymbol{\tau}) \rangle = \langle \boldsymbol{\varpi} : \bar{\boldsymbol{\varepsilon}} \rangle \stackrel{\text{def}}{=} \ell(\boldsymbol{\varpi})$$

- $\boldsymbol{\tau}$: **trial** function (stress-polarization),
- $\boldsymbol{\varpi}$: **test** function (stress-polarization),
- \mathbb{V} : space of second-rank, symmetric tensors fields with square integrable components [BD12].

Discretization of the Lippmann–Schwinger equation

- Galerkin discretization
- The approximation subspace
- The discrete variational problem
- Structure of the underlying linear system

Galerkin discretization in a nutshell

The initial problem

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that $a(\boldsymbol{\tau}, \boldsymbol{\omega}) = \ell(\boldsymbol{\omega})$ for all $\boldsymbol{\omega} \in \mathbb{V}$

Exhaustive exploration of \mathbb{V} is not possible!

Explore a finite-dimension subspace $\mathbb{V}^h \subset \mathbb{V}$

Find $\boldsymbol{\tau}^h \in \mathbb{V}^h$ such that $a(\boldsymbol{\tau}^h, \boldsymbol{\omega}^h) = \ell(\boldsymbol{\omega}^h)$ for all $\boldsymbol{\omega}^h \in \mathbb{V}^h$

This is a linear system!

Our roadmap

- **Define** the approximation subspace \mathbb{V}^h
- **Evaluate** the linear form ℓ over \mathbb{V}^h
- **Evaluate** the bilinear form a over \mathbb{V}^h

Defining the approximation subspace (1/2)

Discretization over a grid


- Any mesh would do...but we anticipate on the use of FFTs!
- **Regular grid:** $N_1 \times \dots \times N_d$
- Grid spacing: $h_i = L_i/N_i$; Total number of cells: $N = N_1 \dots N_d$
- Convention: p, q cell indices (pixels); m, n frequency indices.

Cell average

$$\langle Q \rangle_p \stackrel{\text{def}}{=} \frac{1}{|\Omega_p|} \int_{\Omega_p} Q(\mathbf{x}) \, d\mathbf{x}$$

Average over whole unit-cell

$$\langle Q \rangle = \frac{1}{N} \sum_{p=0}^{N-1} \langle Q \rangle_p$$



Defining the approximation subspace (2/2)

Two natural choices for square-integrable fields

- Trigonometric polynomials
(outside the scope of this talk, see [VZM14; VZM15; Von16])
- Cell-wise constant functions

$$\mathcal{N}_{\text{dofs}} = \dim \mathbb{V}^h = sN \quad s = d(d+1)/2$$

Some technical details

- Trial and test stress-polarization defined by their cell-values

$$\mathbf{x} \in \Omega_p : \quad \boldsymbol{\tau}^h(\mathbf{x}) = \boldsymbol{\tau}_p^h \quad \text{and} \quad \boldsymbol{\omega}^h(\mathbf{x}) = \boldsymbol{\omega}_p^h$$

- Cell-averages

$$\langle \boldsymbol{\tau}^h \rangle_p = \boldsymbol{\tau}_p^h \quad \text{and} \quad \langle \boldsymbol{\omega}^h \rangle_p = \boldsymbol{\omega}_p^h$$

Evaluating ℓ and a over \mathbb{V}^h

$$\left. \begin{aligned} \ell(\mathfrak{w}) &= \langle \mathfrak{w} \rangle : \bar{\boldsymbol{\varepsilon}} \\ \langle \mathfrak{w}^h \rangle_p &= \mathfrak{w}_p^h \end{aligned} \right\} \Rightarrow \ell(\mathfrak{w}^h) = \frac{1}{N} \sum_p \mathfrak{w}_p^h : \bar{\boldsymbol{\varepsilon}}$$

Evaluating a over \mathbb{V}^h

$$a(\boldsymbol{\tau}^h, \boldsymbol{\omega}^h) = \langle \boldsymbol{\omega}^h : \mathbf{M} : \boldsymbol{\tau}^h \rangle + \langle \boldsymbol{\omega}^h : \Gamma_0(\boldsymbol{\tau}^h) \rangle$$

$$\langle \boldsymbol{\omega}^h : \mathbf{M} : \boldsymbol{\tau}^h \rangle = \frac{1}{N} \sum_p \langle \boldsymbol{\omega}^h : \mathbf{M} : \boldsymbol{\tau}^h \rangle_p = \frac{1}{N} \sum_p \boldsymbol{\omega}_p^h : \langle \mathbf{M} \rangle_p : \boldsymbol{\tau}_p^h$$

$$\langle \boldsymbol{\omega}^h : \Gamma_0(\boldsymbol{\tau}^h) \rangle = \frac{1}{N} \sum_p \langle \boldsymbol{\omega}^h : \Gamma_0(\boldsymbol{\tau}^h) \rangle_p = \frac{1}{N} \sum_p \boldsymbol{\omega}_p^h : \langle \Gamma_0(\boldsymbol{\tau}^h) \rangle_p$$

The discrete Green operator

For $\boldsymbol{\tau}^h \in \mathbb{V}^h$, $(\boldsymbol{\tau}_1^h, \boldsymbol{\tau}_2^h, \dots) \mapsto \langle \Gamma_0(\boldsymbol{\tau}^h) \rangle_p$ is linear with respect to the $\boldsymbol{\tau}_p^h$

$$\langle \Gamma_0(\boldsymbol{\tau}^h) \rangle_p = \sum_q \Gamma_{0,pq}^h : \boldsymbol{\tau}_q^h$$

$-\Gamma_{0,pq}^h : \boldsymbol{\tau}_q^h =$ average strain in cell p induced
by constant eigenstress $\boldsymbol{\tau}_q^h$ in cell q !

The discrete variational problem

The discrete variational problem

Find $\tau_0^h, \tau_1^h, \dots, \tau_{N-1}^h$ such that, for all $\varpi_0^h, \varpi_1^h, \dots, \varpi_{N-1}^h$

$$\sum_p \varpi_p^h : \langle \mathbf{M} \rangle_p : \tau_p^h + \sum_{p,q} \varpi_p^h : \Gamma_{0,pq}^h : \tau_q^h = \sum_p \varpi_p^h : \bar{\boldsymbol{\varepsilon}}$$

The linear system

$$\langle \mathbf{M} \rangle_p : \tau_p^h + \sum_q \Gamma_{0,pq}^h : \tau_q^h = \bar{\boldsymbol{\varepsilon}}$$

Convergence w.r.t grid-size

OK, classical Galerkin setting [BD12]

Assembling the linear system

The linear system

$$\langle \mathbf{M} \rangle_p : \boldsymbol{\tau}_p^h + \sum_q \Gamma_{0,pq}^h : \boldsymbol{\tau}_q^h = \bar{\boldsymbol{\varepsilon}} \quad \Leftrightarrow \quad A \cdot x = b$$

Use the Mandel–Voigt representation

- $\langle \mathbf{M} \rangle_p, \Gamma_{0,pq}^h$: fourth-rank tensors $\rightarrow s \times s$ blocks
- $\boldsymbol{\tau}_p^h$ and $\bar{\boldsymbol{\varepsilon}}$: second-rank tensors $\rightarrow s \times 1$ blocks

$$x_p = [\boldsymbol{\tau}_p] \quad \text{and} \quad b_p = [\bar{\boldsymbol{\varepsilon}}]$$


$$A_{pq} = \underbrace{\delta_{pq} [\langle \mathbf{M} \rangle_q]}_{\text{block-diagonal}} + \underbrace{[\Gamma_{0,pq}^h]}_{\text{full matrix!}}$$

A diagram illustrating the assembly of the linear system $A \cdot x = b$. Matrix A is represented as a 3x3 grid of blocks. Vector x is a 3x1 column of blocks. Vector b is a 3x1 column of blocks. The equation is shown as $A \cdot x = b$.

On the structure of the matrix

$$A_{pq} = \delta_{pq}[\langle \mathbf{M} \rangle_q] + [\Gamma_{0,pq}^h] \quad \Leftrightarrow \quad A = D + C.$$

- D : **block-diagonal**
- $\Gamma_{0,pq}^h$: influence of cell q over cell p
- Translation invariant in periodic setting $\Rightarrow C$: **block-circulant!**
- Convolution product in real space \rightarrow local product in Fourier space (here comes the **discrete Fourier transform!!!**)



Connexion with the discrete Fourier transform

- Expression of the discrete Green operator
- Matrix-free implementation
- Wait a minute...

Expression of the discrete Green operator

Exact for cell-wise constant stress-polarizations!

$$\langle \Gamma_0(\boldsymbol{\tau}^h) \rangle_p = \text{DFT}_p^{-1}[\hat{\boldsymbol{\eta}}_\bullet^h], \quad \text{with} \quad \hat{\boldsymbol{\eta}}_n^h = \hat{\Gamma}_{0,n}^h : \hat{\boldsymbol{\tau}}_n^h \quad \text{and} \quad \hat{\boldsymbol{\tau}}_n^h = \text{DFT}_n[\boldsymbol{\tau}_\bullet^h]$$

$$\hat{\Gamma}_{0,n}^h = \sum_{m \in \mathbb{Z}^d} [F(h\mathbf{k}_{n+mN})]^2 \hat{\Gamma}_0(\mathbf{k}_{n+mN})$$

$$F(\mathbf{K}) = \text{sinc} \frac{K_1}{2} \cdots \text{sinc} \frac{K_d}{2}$$

$$\mathbf{k}_{n+mN} = 2\pi \left(\frac{n_1 + m_1 N_1}{L_1} \mathbf{e}_1 + \cdots + \frac{n_d + m_d N_d}{L_d} \mathbf{e}_d \right)$$

Proof is not difficult, but technical [[BD10](#); [BD12](#)]

Wait a minute...

The consistent discrete Green operator

$$\hat{\Gamma}_{0,n}^h = \sum_{m \in \mathbb{Z}^d} [F(h\mathbf{k}_{n+mN})]^2 \hat{\Gamma}_0(\mathbf{k}_{n+mN})$$

Above expression is exact, but its evaluation is difficult, if possible at all [BD10]!

Introduce an approximation of this operator (asymptotically consistent discretization)

Consistent vs. asymptotically consistent discretizations

- What is a variational crime?
- Asymptotically consistent approx. of local operator
- Asymptotically consistent approx. of non-local operator

On variational crimes

The initial problem

Find $\boldsymbol{\tau} \in \mathbb{V}$ such that $a(\boldsymbol{\tau}, \boldsymbol{\omega}) = \ell(\boldsymbol{\omega})$ for all $\boldsymbol{\omega} \in \mathbb{V}$

Exhaustive exploration of \mathbb{V} is not possible!

Consistent discretization

Find $\boldsymbol{\tau}^h \in \mathbb{V}^h$ such that $a(\boldsymbol{\tau}^h, \boldsymbol{\omega}^h) = \ell(\boldsymbol{\omega}^h)$ for all $\boldsymbol{\omega}^h \in \mathbb{V}^h$

Exact evaluation of the bilinear and linear forms!

Asymptotically consistent discretization

Find $\boldsymbol{\tau}^h \in \mathbb{V}^h$ such that $a^h(\boldsymbol{\tau}^h, \boldsymbol{\omega}^h) = \ell^h(\boldsymbol{\omega}^h)$ for all $\boldsymbol{\omega}^h \in \mathbb{V}^h$

Approximations ℓ^h and a^h must be asymptotically consistent [EG04]

We are all criminals

Examples of variational crimes (FEM)

The bilinear form


$$a(\mathbf{u}, \mathbf{v}) = \int_{\Omega} \mathbf{grad}[\mathbf{u}] : \mathbf{C} : \mathbf{grad}[\mathbf{v}]$$

Geometry

$$\bigcup_e \Omega_e \neq \Omega$$

Quadrature

$$\int_{\Omega_e} \mathbf{grad}[\mathbf{u}] : \mathbf{C} : \mathbf{grad}[\mathbf{v}] \simeq \sum_g w_g \mathbf{grad}[\mathbf{u}](\mathbf{x}_g) : \mathbf{C} : \mathbf{grad}[\mathbf{v}](\mathbf{x}_g)$$



Handling heterogeneous cells

Consistent equivalent stiffness of cell [BD12]

$$\begin{aligned}\langle \boldsymbol{\varpi}^h : \mathbf{M} : \boldsymbol{\tau}^h \rangle &= \frac{1}{N} \sum_p \boldsymbol{\varpi}_p^h : \langle \mathbf{M} \rangle_p : \boldsymbol{\tau}_p^h \\ &= \frac{1}{N} \sum_p \boldsymbol{\tau}_p^h : (\mathbf{C}_p^h - \mathbf{C}^{\text{ref}})^{-1} : \boldsymbol{\varpi}_p^h\end{aligned}$$

$$\mathbf{C}_p^h \stackrel{\text{def}}{=} \mathbf{C}^{\text{ref}} + \langle \mathbf{M} \rangle_p^{-1}$$

Although consistent, this rule sometimes leads to surprising convergence results in practice.

Alternative, non-consistent rules

- “Black-or-white”: $\mathbf{C}_p^h =$ stiffness at cell center
- Laminate approximation [KMS15]: probably your best bet

Discrete Green operators

The consistent discrete Green operator

$$\langle \Gamma_0(\boldsymbol{\tau}^h) \rangle_p = \text{DFT}_p^{-1}[\hat{\boldsymbol{\eta}}_\bullet^h], \quad \text{with} \quad \hat{\boldsymbol{\eta}}_n^h = \hat{\Gamma}_{0,n}^{h,c} : \hat{\boldsymbol{\tau}}_n^h$$

$$\hat{\Gamma}_{0,n}^{h,c} = \sum_{m \in \mathbb{Z}^d} [F(h\mathbf{k}_{n+mN})]^2 \hat{\Gamma}_0(\mathbf{k}_{n+mN})$$

Asymptotically consistent discrete Green operators

Retain the nice block-circulant structure!

$$\langle \Gamma_0(\boldsymbol{\tau}) \rangle_p \simeq \text{DFT}_p^{-1}[\hat{\boldsymbol{\eta}}_\bullet^h], \quad \text{with} \quad \hat{\boldsymbol{\eta}}_n^h = \hat{\Gamma}_{0,n}^{h,\star} : \hat{\boldsymbol{\tau}}_n^h$$

Signal processing approaches

Filter out high frequencies!

Rectangular window [MS94; MS98]

Select $m_i \in \{-1, 0\}$ that minimizes $n_i + m_i N_i$

$$\hat{\Gamma}_{0,n}^{h,MS} = \hat{\Gamma}_0(\mathbf{k}_{n+mN}) \quad \text{with} \quad m_i = \begin{cases} -1 & \text{if } 2n_i > N_i \\ 0 & \text{otherwise} \end{cases}$$

If any of the n_i is such that $2n_i = N_i$, then set $\hat{\Gamma}_{0,n}^{h,MS} = \mathbf{C}_0$.

Cosine window [BD12]

$$\hat{\Gamma}_{0,n}^{h,BD} = \sum_{m \in \{-1,0\}^d} [G(h\mathbf{k}_{n+mN})]^2 \hat{\Gamma}_0(\mathbf{k}_{n+mN}) \quad G(\mathbf{K}) = \cos \frac{K_1}{4} \cdots \cos \frac{K_d}{4}$$

Strong connexion w. **band-limited** approximation of Zeman et al. [Zem+10] and Vondřejc [Von16]

Discretization in the real space

Discretize the homogeneous, eigenstressed problem!

Finite differences on rotated grids [Wil15; SOK15]


$$\hat{\Gamma}_{0,n}^{h,\star} = \hat{\Gamma}_0(\mathbf{k}_n^\star) \quad \left\{ \begin{array}{l} \mathbf{k}_n^W = \frac{1}{h_1} \tan \frac{\pi n_1}{N_1} \mathbf{e}_1 + \dots + \frac{1}{h_3} \tan \frac{\pi n_3}{N_3} \mathbf{e}_3 \\ \mathbf{k}_n^{\text{SOK}} = \frac{e^{i2\pi n_1/N_1} - 1}{h_1} \mathbf{e}_1 + \dots + \frac{e^{i2\pi n_3/N_3} - 1}{h_3} \mathbf{e}_3 \end{array} \right.$$

See also Willot and Pellegrini [WP08] and Willot et al. [WAP14]
The above, more operational formula for \mathbf{k}_n^W is proved in [Bri17]


Finite elements [SMK17; Bri17]

No closed-form expression, but fairly easy implementation.


Comparison in Fourier space



Moulinec and Suquet [MS98]



Brisard and Dormieux
[BD12]



Willot [Wil15]

Comparison for impulse



Moulinec and Suquet [MS98]



Brisard and Dormieux
[BD12]



Willot [Wil15]

Which operator should I use?

Moulinec and Suquet [MS98]

Pros: cheap, no dependency on \mathbf{C}_0

Cons: strong Gibbs

Brisard and Dormieux [BD12]

Pros: virtually no Gibbs

Cons: costly, dependency on \mathbf{C}_0

Willot [Wil15] (recommended)

Pros: quite cheap, no dependency on \mathbf{C}_0

Cons: slight Gibbs

Schneider et al. [SMK17]

Pros: no dependency on \mathbf{C}_0
Gibbs?

Cons: quite costly

Conclusion

- Weak form of the Lippmann–Schwinger equation
- Galerkin discretization (cell-wise constant test functions)
- Consistent discretization impractical
- Introduce several asymptotically consistent discretizations

The problem is now ready to be handed to a solver!

References

- [BD10] S. Brisard and L. Dormieux. “FFT-Based Methods for the Mechanics of Composites: A General Variational Framework.” In: *Computational Materials Science* 49.3 (2010), pp. 663–671.
- [BD12] S. Brisard and L. Dormieux. “Combining Galerkin Approximation Techniques with the Principle of Hashin and Shtrikman to Derive a New FFT-Based Numerical Method for the Homogenization of Composites.” In: *Computer Methods in Applied Mechanics and Engineering* 217–220 (2012), pp. 197–212.
- [Bri17] S. Brisard. “Reconstructing Displacements from the Solution to the Periodic Lippmann–Schwinger Equation Discretized on a Uniform Grid.” In: *International Journal for Numerical Methods in Engineering* 109.4 (2017), pp. 459–486.
- [BS18] C. Bellis and P. Suquet. “Geometric Variational Principles for Computational Homogenization.” In: *Journal of Elasticity* (2018).
- [EG04] A. Ern and J.-L. Guermond. *Theory and Practice of Finite Elements*. Applied Mathematical Sciences. New York: Springer-Verlag, 2004.
- [KMS15] M. Kabel et al. “Use of Composite Voxels in FFT-Based Homogenization.” In: *Computer Methods in Applied Mechanics and Engineering* 294 (2015), pp. 168–188.
- [Kor73] J. Korringa. “Theory of Elastic Constants of Heterogeneous Media.” In: *Journal of Mathematical Physics* 14.4 (1973), pp. 509–513.

- [Krö74] E. Kröner. “On the Physics and Mathematics of Self-Stresses.” In: *Topics in Applied Continuum Mechanics*. Ed. by J. L. Zeman and F. Ziegler. Vienna: Springer Verlag Wien, 1974, pp. 22–38.
- [MS94] H. Moulinec and P. Suquet. “A Fast Numerical Method for Computing the Linear and Nonlinear Mechanical Properties of Composites.” In: *Comptes rendus de l’Académie des sciences. Série II, Mécanique, physique, chimie, astronomie* 318.11 (1994), pp. 1417–1423.
- [MS98] H. Moulinec and P. Suquet. “A Numerical Method for Computing the Overall Response of Nonlinear Composites with Complex Microstructure.” In: *Computer Methods in Applied Mechanics and Engineering* 157.1–2 (1998), pp. 69–94.
- [SMK17] M. Schneider et al. “FFT-Based Homogenization for Microstructures Discretized by Linear Hexahedral Elements.” In: *International Journal for Numerical Methods in Engineering* 109.10 (2017), pp. 1461–1489.
- [SOK15] M. Schneider et al. “Computational Homogenization of Elasticity on a Staggered Grid.” In: *International Journal for Numerical Methods in Engineering* (2015), n/a–n/a.
- [Von16] J. Vondřejc. “Improved Guaranteed Computable Bounds on Homogenized Properties of Periodic Media by the Fourier–Galerkin Method with Exact Integration.” In: *International Journal for Numerical Methods in Engineering* 107.13 (2016), pp. 1106–1135.
- [VZM14] J. Vondřejc et al. “An FFT-Based Galerkin Method for Homogenization of Periodic Media.” In: *Computers & Mathematics with Applications* 68.3 (2014), pp. 156–173.

- [VZM15] J. Vondřejc et al. “Guaranteed Upper–Lower Bounds on Homogenized Properties by FFT-Based Galerkin Method.” In: *Computer Methods in Applied Mechanics and Engineering* 297 (2015), pp. 258–291.
- [WAP14] F. Willot et al. “Fourier-Based Schemes with Modified Green Operator for Computing the Electrical Response of Heterogeneous Media with Accurate Local Fields.” In: *International Journal for Numerical Methods in Engineering* 98.7 (2014), pp. 518–533.
- [Wil15] F. Willot. “Fourier-Based Schemes for Computing the Mechanical Response of Composites with Accurate Local Fields.” In: *Comptes Rendus Mécanique* 343.3 (2015), pp. 232–245.
- [Wil77] J. Willis. “Bounds and Self-Consistent Estimates for the Overall Properties of Anisotropic Composites.” In: *Journal of the Mechanics and Physics of Solids* 25.3 (1977), pp. 185–202.
- [WP08] F. Willot and Y.-P. Pellegrini. *Fast Fourier Transform Computations and Build-up of Plastic Deformation in 2D, Elastic-Perfectly Plastic, Pixelwise Disordered Porous Media*. arXiv e-print 0802.2488. in D. Jeulin, S. Forest (eds), “Continuum Models and Discrete Systems CMDS 11”, (Ecole des Mines, Paris, 2008), pp. 443-449. [ISBN: 978-2-356-71000-0]. 2008.
- [ZD73] R. Zeller and P. H. Dederichs. “Elastic Constants of Polycrystals.” In: *Physica Status Solidi (B)* 55.2 (1973), pp. 831–842.

- [Zem+10] J. Zeman et al. “Accelerating a FFT-Based Solver for Numerical Homogenization of Periodic Media by Conjugate Gradients.” In: *Journal of Computational Physics* 229.21 (2010), pp. 8065–8071.

Thank you for your attention

`sebastien.brisard@univ-eiffel.fr`

`https://navier-lab.fr/en/equipe/brisard-sebastien`

`https://cv.archives-ouvertes.fr/sbrisard`

`https://sbrisard.github.io`



This work is licensed under the Creative Commons Attribution 4.0 International License. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/> or send a letter to Creative Commons, PO Box 1866, Mountain View, CA 94042, USA.